

Exterior 100% Acrylic Medium-Build Elastomeric Coating Architectural Coating - Premium Plus

Description

A premium plus 100% acrylic medium-build elastomeric coating, designed for use on exterior concrete, stucco, plaster, masonry and wood including T-111 siding & other properly prepared vertical surfaces. Exhibits outstanding performance with good elasticity and elongation characteristics. Resists mildew and dirt pick-up with excellent color retention.

Recommended Uses

New or previously painted concrete, Masonry, plaster, stucco, brick and wood.

Colors

White and custom colors to order
Bases: White, A, D, & P (Factory-Tint)

Packaging

Five gallon containers

Finish

Flat with slight angular sheen, available in coarse, medium & fine texture. Sheen @ 85° = 2.8 - 3.2%

Surface Preparation

All contaminants that may impair adhesion must be removed (i.e. sacking dust, grade marks, grease and loose scale). It is important that new stucco and concrete be cured prior to starting the work. Check for alkalinity on surface. Washing with mild acid, such as a phosphoric (Ked) or salicylic acid may be required. All cracks, voids, joints or other imperfections should be repaired using the appropriate Vista Paint patching compounds and caulking sealants.

Primer

Concrete Masonry and Stucco (New):	4600 Uniprime II
Wood (New):	8600 Polytec Primer
	4200 Terminator II
	8000 Carefree Prime-ZALL (for problem surfaces)
	8600 Polytec Primer

Application

Brush, roll or spray. Ambient and surface temperatures must be above 55°F and relative humidity below 80%. Clean tools and equipment with soap and water.

Drying Time

Touch:	2 hours
Recoat:	8 hours

Coverage

Up to 150 square feet per gallon, depending on porosity and texture of the surface.

Mil Thickness

Wet = 14.0 - 18.6 Dry = 6 - 8

Thinning

Use at package consistency. If thinning is required, use water sparingly.

Composition

Titanium Dioxide	9.0%
Extenders	30.1%
TOTAL PIGMENT	39.1%
Acrylic Resin	22.0%
Additives	5.7%
Water	33.1%
TOTAL VEHICLE	60.9%

Weights & Measurements +/-3.0%

Solids by Volume:	47.4%
Solids by Weight:	64.1%
VOC:	45 g/l
Weight Per Gal:	11.9 lbs.
Viscosity:	110 - 116 KU

Room Temperature Testing

Tensile Strength
ASTM D 2370 @ 75°F 650 psi

Elongation
ASTM D 2370 @ 75°F 190%

Water Vapor Permeance
ASTM 1653 @ 75°F 7.2 perm

Weather Resistance
After 2,000 hours weather-o-meter (ASTM-D822), no deterioration or chalking.

Conformance

SCAQMD - complies with Rule 1113, Architectural Coatings.

MPI - #40

Federal Specification - Passes TT-C-555B Wind Driven Rain.



Products bearing this logo are Non-EG Certified. Ethylene Glycol (EG), is listed as a toxic air contaminant and hazardous pollutant. EG is a solvent used in some water-based paints. Vista Paint has replaced EG with non-toxic alternative solvents. Any Vista Paint product with this logo is formulated without EG (Non-EG).



Vista Paint is the industry leader when it comes to relying on renewable energy. At Vista Paint, our products are manufactured using 100% solar energy.

04.2023

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.

