

Acriglo Semi-Gloss

7040

Interior / Exterior Zero* VOC, 100% Acrylic Enamel Finish

Architectural Coating - Premium Plus

Description

Acriglo Semi-Gloss is a premium plus zero* VOC 100% acrylic semi-gloss enamel for interior and exterior surfaces. This product provides good block resistance and durability. Acriglo has good adhesion and mildew resistant characteristics. Its low odor makes it suitable for institutional, commercial and residential applications.

NOTE: This product contains ingredients which resist the growth of mircrobes on the surface of the paint film.

Recommended Uses

Properly primed drywall, concrete, masonry, wood and metal.

Colors

White and custom colors Bases: A, D, & P

Packaging

One and five gallon containers

Finish

Semi-Gloss sheen at 60° = 60.0 - 64.0%MPI sheen level #5

Surface Preparation

Surfaces must be clean, dry and free from all contaminants that may impair adhesion. Smooth wood and glossy or slick surfaces must be scuff sanded prior to application of paint coatings and may require priming.

Primer

Drywall (New): 1100 Hi-Build Sealer
Drywall (Existing): 4000 Uniprime
Concrete/Masonry: 4600 Uniprime II
Wood (Exterior): 4000 Uniprime
Wood (Interior): 4000 Uniprime
8000 Prime-ZALL

Ferrous Metal: 9600 Protec Metal Prime White

9610 Protec Metal Prime Red Oxide

Galvanized: 4800 Metal Pro Primer White

4810 Metal Pro Primer Red Oxide 8600 Polytec Primer White 8610 Polytec Primer Red Oxide

Aluminum 8600 Polytec Primer

Application

Brush, roll or spray. Ambient and surface temperatures must be above 55°F and relative humidity below 80%. Clean tools and equipment with soap and water.

Drying Time

Touch: 2 hours Recoat: 4 hours

<u>Coverage</u>

Up to 400 square feet per gallon, depending on porosity and texture of the surface.

Mil Thickness

Wet = 4.8 Dry = 1.6

Thinning

DO NOT THIN

Composition

TOTAL VEHICLE

Titanium Dioxide	14.4%
Extenders	1.2%
TOTAL PIGMENT	15.6%
Acrylic Resin	21.7%
Additives	2.5%
Water	54.8%

Weights & Measurements +/-3.0%

Solids by Volume: 35.0% Solids by Weight: 46.0% VOC: <2 g/l Weight Per Gal: 10.2 lbs. Viscosity: 94 - 98 KU

Conformance

SCAQMD - complies with Rule 1113, Architectural Coatings. **CDPH Section 01359** - Standard Method V1.2 2017

84.4%

LEED - Complies with LEEDv4

MPI - #54, #147

*NOTE: Zero VOC is defined as no VOC containing solvents added in the manufacturing process of this product. Slight traces of VOC are present in additives used in manufacturing. This product has less than half the allowable VOC of the SCAQMD Super Compliant Coatings category.

*NOTE: This product complies with the Super Compliant Coatings category under SCAQMD definitions.



Vista Paint is committed to safer, more environmentally responsible products. Our paint formulas are PFAS-free* and contain no perfluoroalkyl or polyfluoroalkyl substances—commonly known as "forever chemicals"—which are linked to environmental and health concerns due to their resistance to natural breakdown.



Products bearing this logo are Non-EG Certified. Ethylene Glycol (EG), is listed as a toxic air contaminant and hazardous pollutant. EG is a solvent used in some water-based paints. Vista Paint has replaced EG with non-toxic alternative solvents. Any Vista Paint product with this logo is formulated without EG (Non-EG).



Vista Paint is the industry leader when it comes to relying on renewable energy. At Vista Paint, our products are manufactured using 100% solar energy.

Updated 10.2025

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.